



MOMENTIVE

performance materials

TPG[®] Thermal Management Material

TPG (thermal pyrolytic graphite) is a unique form of pyrolytic graphite manufactured from thermal decomposition of hydrocarbon gas in a high temperature chemical vapor deposition reactor.

Benefits

- Thermal conductivity to 4 times copper
- Lighter than aluminum
- Compatible with many encapsulating techniques
- Sizes from dies and packages to PWB's
- Passive, high performance heat transfer


Features

- Highly oriented crystals in a layered structure
- In-plane conductivity typically 1350 to 1700 watts/m-K
- Fully dense ceramic
- High c-direction modulus, contributing to improved section properties in composite structures
- Layered structure avoids brittle, catastrophic failure
- Easily machined, provided as plates or as final shapes
- Thickness ranges from less than 0.010" (0.25 mm) to over 0.200" (5 mm)
- Plate sizes up to 5" (125 mm) x 20" (500 mm)
- Special sizes can usually be provided upon request

Applications

The high thermal conductivity of TPG comes from a crystal structure that usually requires capturing the TPG material in some structural member. Final products typically include encapsulations such as aluminum, copper, AISiC and carbon fiber composite to solve thermal problems in such needs as:

- Heat spreaders in packages
- Thermal cores for PWB's
- Heat spreaders for improved performance of finned sinks
- Laser diode mounts




ITRS Impact - The International Technology Roadmap for Semiconductors shows power dissipation increasing by 10 watts per year from 130 watts in 2002 at the 130 nm node to 160 watts in 2005 at the 100 nm node. TPG can enable transparent thermal solutions without the need for dramatic changes in fans or forced cooling.

Typical TPG Properties


Thermal Conductivity	1500 <20	Watts/m-K, a-b axis Watts/m-K, c axis
Density	2.26	gm/cc
Thermal Expansion Coefficient	0 to -1 25	ppm/°C, a-b axis ppm/°C, c axis
Specific Heat	0.71	J/gm-°C @ 25° C
Flexural Strength	36.7 38.5	+/-4%, MPa, ab +/-4%, MPa, ab
Stiffness	1050 36	+/-2%, GPa, c ₁₁ +/-3%, GPa, c ₃₃
Compressive Strength	nil	ab
Tensile Strength	nil	ab

Typical Thermal Performance




TPG shows over 5X the power dissipation capability of aluminum

Thermal Images



6061 Aluminum
T_{max} = 115°C



TPG
T_{max} = 44°C

www.momentive.com

SALES OFFICES

USA

T: 440.878.5700
F: 440.878.5928
E: cs-na.ceramics@momentive.com

GERMANY

T: 49.4152.9380
F: 49.4152.938.136
E: cs-eur.ceramics@momentive.com

JAPAN

T: 81.3.5114.3774
F: 81.3.5114.3779
E: cs-jp.ceramics@momentive.com

CHINA

T: 86.21.6288.1088
F: 86.21.6289.0681
E: cs-asia.ceramics@momentive.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC., MOMENTIVE PERFORMANCE MATERIALS USA INC., MOMENTIVE PERFORMANCE MATERIALS ASIA PACIFIC PTE. LTD., MOMENTIVE PERFORMANCE MATERIALS WORLDWIDE INC., MOMENTIVE PERFORMANCE MATERIALS GmbH & Co. KG, MOMENTIVE PERFORMANCE MATERIALS SUISSE Sarl, THEIR SUBSIDIARIES AND AFFILIATES DOING BUSINESS IN LOCAL JURISDICTIONS (collectively "SUPPLIERS"), ARE SOLD BY THE RESPECTIVE LEGAL ENTITY OF THE SUPPLIER SUBJECT TO SUPPLIERS' STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIERS MAKE NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SUPPLIERS' PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. AFOREMENTIONED EXCLUSIONS OR LIMITATION OF LIABILITY ARE NOT APPLICABLE TO THE EXTENT THAT THE END-USE CONDITIONS AND/OR INCORPORATION CONDITIONS CORRESPOND TO THE RECOMMENDED CONDITIONS OF USE AND/OR OF INCORPORATION AS DESCRIBED BY SUPPLIER IN ITS PRODUCT DATA SHEET AND/OR PRODUCT SPECIFICATIONS. EXCEPT AS PROVIDED IN SUPPLIERS' STANDARD CONDITIONS OF SALE, SUPPLIERS AND THEIR REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Suppliers' materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Suppliers' products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Suppliers' Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Suppliers. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Suppliers or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.